



TECHNICAL DATA SHEET (TDS)

Exflam APP 201

Equivalent to: Exolit AP 422 from Clariant

FR Cros 484 from Budenheim

Product name:

Ammonium polyphosphate n>1000, Phase II

Specification:

Phosphorus, % wt	min 31
Nitrogen, % wt	min 14
PH value (10% suspension)	5.5-7.0
Water content %(w/w).....	max 0.25
Thermal decomposition, °C	min 275
Viscosity @25 °C in 10% suspension, mPa.s	max 50
Solubility in water (g/100cm ³), % wt	max 0.5
Average particle size, um	max 15

Application:

Be used in intumescent coatings, adhesive and sealants. Polyurethane foam, PU rigid, PU rigid integral skin foam, PU flexible. It can be used in cellulose-containing material (paper, wood). Meanwhile, this grade can also be used in casting resin based on epoxy resin, unsaturated PE resin, thermoplastics Plastic etc.

Shipping Information:

The package is 25kg craft paper bag, 875kg big bag or on customer's request.

1*20FCL can be loaded 20mt with 25kg bag on pallet or 17.5mt with 875kg bag on pallet.

Hazards identification: None.

The substance is not subject to IMO TMDG.

The information supplied is presented in good faith and has been derived from sources believed to be reliable. Since conditions of use are beyond our control, user assumes all risks. No representation is expressed or implied, and nothing herein shall be construed as permission or recommendation to practice a patented invention without license