

MP 150HMR

CAS No: 9004-65-3

Product Description

Constitution	Modified Methyl HydroxyPropyl Cellulose		
Appearance	Powder	Delayed solubility	Yes
Etherification	Standard etherification	Modification	Moderate

Product Specification

Moisture, as packed	≤5.0%	Recommend application
Ash content, as Na ₂ SO ₄	≤2.0%	
Particle size	<0.200 mm: min.98.5 %	
Particle size	<0.180 mm: min.90.0%	Plasters, cement based
PH (1% solution)	6.0-7.5	Tile adhesive
Viscosity		
1.9% absolutely dry, 20±0.1°C,	60,000-70,000mPa.s	
20°GH Brookfield RV, 20 rpm, sp. 7		

Application performance

Consistency development	Fast	Water retention	High
Final consistency	High	Influence on cement hydration	Moderate
Sag resistance	High	Heat stability	High
Water demand	High		

Safety Notice:

Read and understand the Material Safety Data Sheet (MSDS) before handling this product. All MSDS sheet is available for download from www.wekcelo.com

PACKAGING AND STORAGE:

WeKcelo® is supplied in multi-ply paper bags with polyethylene intermediate layer, containing 25 kgs; shrink palletizing is available by ordering a minimum quantity of 600 kgs.

WeKcelo® has a long shelf life (minimum 12 months) stored in dry, normal temperature condition and no direct sun shine.

For more exact information, please contact local our sales representative and your local authorized distributor.

Date of Issue: 15th Dec, 2011

This product specification information is based on our present state of knowledge and to provide general notes on our products and application. It should therefore not be construed as guaranteeing specific properties of the products or their suitability for specific application.

This Product Specification is not signed. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. If you have any questions, please contact our R&D center or sales people from WeiKem.