



RADIANT
CHEMICALS

Plot No - A 4, M.I.D.C,
Kulgaon, Badlapur - E,
Dist - Thane (421 503)
State - Maharashtra, INDIA
Ph : +91-251-2696 114.
Fax : +91-251-2696 115.
Email : rhinol@radiantchemicals.com
Web : www.radiantchemicals.com

RHINADISPERS - 163

RHINADISPERS-163 is a wetting and dispersing additive for solvent-borne coatings and pigment concentrates. Stabilizes pigments of all types. Broad compatibility for all-purpose solvent-borne pigment concentrates on the basis of aldehyde and acrylate grinding resins.

Solution of a high molecular weight block copolymer with pigment affinic groups

PRODUCT SPECIFICATION

PROPERTIES	SPECIFICATION
Density (20° C)	0.99 g/ml
Non-Volatile matter (20 min, 150 °C)	Min 45%
Solvents	Xylene/Butylacetate/Methoxypropylacetate
pH (as such)	7.00

Special Note

The after-treatment of some organic pigments may negatively affect the efficiency of the additive. In such cases, tests with the untreated pigment of the same type may be successful. When used in coil coatings, the interaction of this cationic additive with the acid catalyst must be taken into account. Amine-blocked acids are less suitable than free acids or epoxy-blocked acids.

Applications

Coatings Industry

Special Features and Benefits

The additive deflocculates pigments and stabilizes them by means of steric hindrance. It provides equal electrical charge to the pigment particles. The resulting repulsion and the steric stabilization prevent a possible co-flocculation, which leads to flood and float-free color in pigment mixtures. The deflocculating properties of the additive increase gloss, color strength, transparency, and hiding power and reduce the viscosity of the mill base.

Recommended Use

The additive features a broad compatibility and is used in many solvent-borne formulations. It can also be used for retroactive batch correction. For new formulations, we recommend checking the more modern additives .

Recommended Levels

Amount of additive (as supplied) based upon pigment:

Inorganic pigments	:	15.0 - 020.0 %
Titanium dioxide	:	04.0 - 005.0 %
Organic pigments	:	30.0 - 060.0 %
Carbon blacks	:	80.0 - 100.0 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimum performance, the additive must be incorporated into the mill base before addition of pigments. The resin and solvent components of the mill base are pre-mixed and then the additive is slowly incorporated while stirring continuously. Do not add the pigments until the additive has been fully distributed. Post-addition (to repair faulty batches) is possible as long as the product is added slowly and under high shear forces.