

maple[®] FL-2012A
TGIC Polyester Resin

TECHNICAL DATA SHEET

Version : 2022

General Description

FL-2012A is a carboxyl functional polyester resin for combination with TGIC at 93/7

- Outstanding flow
- Tribo charge

Extrusion&Application Conditions

Extruder	Twin screw
Temperature (°C)	105-115
Speed (rpm)	250
Application	0.5mm steel panel
Curing-metal temp.	200°C/10min

Product Specification

Property	Range	Test Method
Appearance	Pale granules	Visual
Color(Pt-Co)	150	GB/T9282.1-2008
Acid value mgKOH/g	30-36	GB/T6473-2008
Viscosity Brookfield, @ 200°C,mPa.s	4200-5400	GB/T9751.1-2008
Tg ,°C	Approx 65	GB/T19466.1-2004

Film Properties

Test	Result	Test Method
Film thickness (μm)	55-75	GB/T13452.2-2008
Gloss @ 60° (%)	≥90	GB/T9754
Direct/reverse impact (Kg.cm)	50/50	GB/T1732-1993

Starting Formulation

Component	Weight/g
FL-2012A	558
TGIC	42
Titanium dioxide	386
Flow agent	10
Benzoin	4

Package

White opaque polyethylene bags of 25kg

Shelf Life

The shelf life of the resin will be one year.
 Stored in a dry place at temperature below 30°C
 Avoid direct sunlight.

Yantai Fenglin Advanced Materials Co., Ltd

Floor 11, Zhongxin Building, No.77 Changjiang Road, Economic and Technological Development Zone, Yantai City

Tel : 0086-535-6935111

Fax : 0086-535-6935188

Web : www.fenglin.com.cn

Emai : info@fenglin.com.cn

Disclaimer: The information contained herein are to the best of our knowledge and reliable. However, we make no warranty of any kind that the product and /or information is adapted for any specific use. Nither Maple nor Maple agent assume any legal responsibility for any loss or damages caused by products. The user should perform its own tests to determine the suitability for its particular purpose and remain the sole responsibility for its usage.