



RADIANT
CHEMICALS

Plot No - A 4, M.I.D.C,
Kulgaon, Badlapur - E,
Dist - Thane (421 503)
State - Maharashtra, INDIA
Ph : +91-251-2696 114 / 115.
Email : rhinol@radiantchemicals.com
Web : www.radiantchemicals.com

RHINADISPERS - 180

Solvent-free wetting and dispersing additive for solvent-borne, solvent-free & aqueous coating systems, printing inks and adhesives for stabilizing inorganic pigments, in particular titanium dioxide.

CHEMICAL COMPOSITION

Alkylol ammonium salt of a copolymer with acidic groups

SPECIFICATIONS

Acid value	:	90 mg KOH / g
Density	:	1.03 gm / ml
Non-volatile matter (10 min., 150 °C)	:	Min 81.0 %
pH (as such)	:	7.0

APPLICATIONS

Coating Industry, Printing Inks and Adhesives

Special Features and Benefits

The additive deflocculates pigments by means of steric stabilization. As a result of the small particle sizes of the deflocculated pigments, high levels of gloss can be achieved and the color strength is improved. Transparency and hiding powder also increase and viscosity is reduced. In this way, the flow characteristics are also improved and higher pigment loading is possible.

Recommended Use

The additive is recommended for all aqueous, solvent-borne and solvent-free systems to stabilize inorganic pigments, specifically titanium dioxide.

Recommended Levels

Amount of additive (as supplied) based upon pigment.

Inorganic pigments : 05.0 - 10.0 %

Titanium dioxides : 1.50 - 2.50 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimum performance, the additive must be incorporated into the millbase before addition of pigments. The resin and solvent components of the millbase are pre-mixed and then the additive is slowly incorporated while stirring continuously. Do not add the pigments until the additive has been fully distributed.